



THE UNIVERSITY *of* EDINBURGH

Edinburgh Research Explorer

Tuning of Structure, Morphology and Magnetism in Postperovskite Oxide Solid Solutions

Citation for published version:

Hirai, S, Sanehira, T, Nishiyama, N, Irifune, T, Klemme, S, Bromiley, G & Attfield, JP 2011, 'Tuning of Structure, Morphology and Magnetism in Postperovskite Oxide Solid Solutions', *Chemistry of Materials*, vol. 23, no. 1, pp. 114-121. <https://doi.org/10.1021/cm102660q>

Digital Object Identifier (DOI):

[10.1021/cm102660q](https://doi.org/10.1021/cm102660q)

Link:

[Link to publication record in Edinburgh Research Explorer](#)

Document Version:

Peer reviewed version

Published In:

Chemistry of Materials

Publisher Rights Statement:

Final publication copyright of the American Chemical Society (2011)

General rights

Copyright for the publications made accessible via the Edinburgh Research Explorer is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The University of Edinburgh has made every reasonable effort to ensure that Edinburgh Research Explorer content complies with UK legislation. If you believe that the public display of this file breaches copyright please contact openaccess@ed.ac.uk providing details, and we will remove access to the work immediately and investigate your claim.



This is the author's final draft or 'post-print' version. The final publication is available online copyright of the American Chemical Society (2011).

Cite As: Hirai, S, Sanehira, T, Nishiyama, N, Irifune, T, Klemme, S, Bromiley, G & Attfield, JP 2011, 'Tuning of Structure, Morphology and Magnetism in Postperovskite Oxide Solid Solutions' *Chemistry of Materials*, vol 23, no. 1, pp. 114-121.

DOI: 10.1021/cm102660q

Tuning of structure, morphology and magnetism in post-perovskite oxide solid solutions

Shigeto Hirai^{*}, Takeshi Sanehira^{**}, Norimasa Nishiyama^{**}, Tetsuo Irifune^{**}, Stephan Klemme^{***}, Geoffrey Bromiley^{*} and J. Paul Attfield^{****}

^{*}Centre for Science at Extreme Conditions and School of Geosciences, University of Edinburgh, Mayfield Road, Edinburgh EH9 3JZ, UK

^{**} Geodynamics Research Center, Ehime University, 2-5 Bunkyo-cho, Matsuyama, Ehime 790-8577, Japan

^{***} Institut für Mineralogie, Corrensstr. 24, Universität Münster, 48149 Münster, Germany

^{****} Centre for Science at Extreme Conditions and School of Chemistry, University of Edinburgh, Mayfield Road, Edinburgh EH9 3JZ, UK

Abstract: High-quality polycrystalline samples of post-perovskite type $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ solid solutions ($x = 0.3, 0.5, 0.7$) and $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ have been synthesised at a pressure of 15 GPa, and their structures and properties are compared to those of CaIrO_3 . Substantial [100] grain growth is observed in all samples leading to pronounced texture even in powdered materials. Small changes in the lattice constants and octahedral distortions are observed in the $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ series, consistent with a reduction in Jahn-Teller activity. CaIrO_3 is semiconducting and shows temperature-independent paramagnetism, and an ordered moment of $0.04 \mu_B$ below a 108 K magnetic transition. Doping with Pt or Rh induces Curie-Weiss paramagnetism and suppresses the magnetic transition, to zero for ~40% Pt doping. The anisotropic structure and morphology of CaIrO_3 combined with the Ir^{4+} spin-orbit coupling result in a large magnetic anisotropy constant of $1.77 \times 10^6 \text{ J m}^{-3}$, comparable to values for permanent magnet materials.

I. Introduction

Since the discovery of the perovskite to post-perovskite transition in MgSiO_3 in a laser-heated diamond anvil cell¹, wide attention has been focussed on the post-perovskite phase of MgSiO_3 . This is because the post-perovskite phase is likely to play a key role in processes occurring in Earth's lower mantle, and the perovskite to post-perovskite transition can explain many features of the D'' seismic discontinuity there. While it is important to conduct further studies on MgSiO_3 , this post-perovskite phase cannot be quenched to ambient conditions; this is also the case for the post-perovskite type transition metal oxides Fe_2O_3 ² and Mn_2O_3 ³. Thus, it is useful to investigate the materials properties of structural analogues of the MgSiO_3 post-perovskite that are quenchable to ambient conditions. The electronic and magnetic properties of transition metal analogues are also of interest as post-perovskite type oxides are rare and their physical properties have not been extensively explored.

The post-perovskite phase of MgSiO_3 adopts the layered CaIrO_3 -type structure containing corner-linked chains of edge-sharing octahedra (Fig.1). Four quenchable CaIrO_3 -type oxides have been reported to date: CaIrO_3 ⁴, CaPtO_3 ⁵, CaRhO_3 ⁶ and CaRuO_3 ⁷. Polycrystalline CaIrO_3 can be synthesized at ambient pressure from binary oxides heated to 1273 K in an evacuated silica tube, and single crystals of CaIrO_3 were synthesized at 1223 K using a CaCl_2 flux.⁴ The other three oxides were obtained using a multi-anvil apparatus to achieve high pressure (P) and temperature (T) conditions; CaPtO_3 (4GPa, 1073K),⁵ CaRhO_3 (6GPa, 1473K)⁶ and CaRuO_3 (23GPa, 1223K).⁷ Further studies on these materials have revealed post-perovskite to perovskite structural phase transitions at high P-T. The post-perovskite phase of CaIrO_3 transforms to the perovskite structure at 2GPa, 1673K⁸ and this transformation was also observed for CaRhO_3 (6GPa, 1873K) and CaRuO_3 (23GPa, 1343K), while CaPtO_3 remained in the post-perovskite structure at higher temperatures⁹. The former observations show that the perovskite type is the high temperature phase for these CaMO_3 post-perovskites, and this was supported by a Raman spectroscopy study of CaIrO_3 up to 30GPa¹⁰ and a synchrotron X-ray diffraction of CaPtO_3 up to 40GPa¹¹ which show that the phase transition from post-perovskite to perovskite transition does not occur at room temperature.

The presence of transition metal ions in the above CaMO_3 post-perovskites suggests that such phases might have interesting electronic or magnetic properties. A study of $\text{Ca}_{1-x}\text{Na}_x\text{IrO}_3$

solid solutions (synthesized at 4GPa, 1073K)¹² revealed a metal-insulator transition at $x = 0.37$. To investigate such properties further, we have explored the $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ series and the synthesis, structural and physical properties of these solid solutions are reported here. We also demonstrate that $\text{CaIr}_{1-x}\text{Rh}_x\text{O}_3$ materials are accessible as we report the $x = 0.5$ member of this series.

II. Experimental Section

Polycrystalline samples of CaIrO_3 post-perovskite were synthesized by solid state reaction from CaO and IrO_2 . CaO powder was prepared from CaCO_3 by heating in air at 1000 °C for 24 hrs. Well-ground mixtures of the starting materials in the stoichiometric ratio were sealed in an evacuated silica tube, and heated in air at 1273K over 20 hrs. CaIrO_3 post-perovskite single crystals were synthesized by a flux method⁴.

Polycrystalline samples of $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ and $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ were synthesized at high pressure-temperature conditions. $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ ($x = 0.3, 0.5, 0.7$) were synthesized by solid-state reaction from CaO , IrO_2 , and PtO_2 powders. Well-ground mixtures of the starting material in a stoichiometric molar ratio were placed into an Au capsule ($\phi = 2.5$ mm) sandwiched by BN composite disks ($\phi = 2.7$ mm). $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ was synthesized by solid-state reaction from CaO , IrO_2 , and Rh_2O_3 , with KClO_4 as an oxidizer. A well-ground mixture of the starting materials at a ratio of 1/0.5/0.5/4.07 (Ca/Ir/Rh/O) was placed into an Au capsule ($\phi = 2.5$ mm) sandwiched by MgO disks ($\phi = 2.7$ mm), to avoid sample reduction. The capsules were heated in a multi-anvil apparatus at 1573 K and 15GPa pressure for 40 min, followed by rapid quenching to ambient temperature, and then release of pressure. A pressure of 15GPa was used to ensure that homogenous solid solutions were formed as reactions at 3 and 10 GPa gave samples with a range of Ir/Pt ratios and containing IrO_2 and Pt secondary phases. Dense black pellets were obtained and that of $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ was washed with distilled water to remove KCl.

Powdered samples were investigated by powder X-ray diffraction (XRD) using a Bruker D8 diffractometer in reflection geometry with monochromated Cu $\text{K}\alpha 1$ radiation. Two patterns were collected for each sample – one from the loosely packed powder and the other from the powder sieved onto a sample holder covered by a thin layer of organic grease, to minimise preferred orientation of crystallites. The GSAS software was used for Rietveld refinement of the crystal structure and texture analysis.¹³ Scanning electron microscopy with energy dispersive X-ray analysis (SEM/EDX) was conducted on a polished surface of selected samples using a Phillips XL30CP, with PGT Spirit X-ray analysis, using an acceleration voltage of 20 kV.

Electrical resistivities of rectangular pellets were studied by a four-point probe method with a gauge current of 0.99 mA. Electrical contacts were made from Cu wires and silver paste.

Magnetisations were measured using a Quantum Design MPMS SQUID magnetometer. Zero field- and field-cooled (ZFC and FC) measurements were made with a field of 100 Oe after cooling the sample to 5 K. Ambient condition Raman spectra on $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ ($x = 0.3, 0.5, 0.7$) and $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ were collected using a Jobin Yvon LabRAM instrument ($\lambda = 632.8 \text{ nm}$).

III. Results

A Structure and Morphology

XRD patterns (Fig. 2) demonstrate that the recovered $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ ($x = 0, 0.3, 0.5, 0.7$) and $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ samples contain post-perovskites with traces of secondary phases in some cases. All of the major XRD peaks are indexed by the CaIrO_3 -type cell with orthorhombic space group $Cmcm$. The Raman spectra are similar to that for CaIrO_3 and the shifts of the five primary Raman modes of $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ series (Table 1) confirm that solid solutions are present. The ν_4 Raman mode is not observed in CaIrO_3 but appears around 563 cm^{-1} for all the Pt or Rh doped samples.

The morphologies and stoichiometries of the samples were examined by SEM/EDX analysis for $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ and by using an electron microprobe for $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ ($x = 0, 0.3, 0.5, 0.7$). Traces of additional elements were not detected for any of the samples in the EDX patterns and the stoichiometries were confirmed as being the same as the nominal compositions. The crystallites show a needle-like morphology in all samples. The growth of needle-like grains elongated in the a -axis direction was previously reported for CaIrO_3 and CaPtO_3 .^{2,3,14} The mean grain size varies in the range $1\text{-}8\mu\text{m}$ between samples as shown in the micrographs in Fig. 3 and as summarised in Table 2. Large grains are also observed for polycrystalline CaIrO_3 post-perovskite, prepared at ambient pressures and temperatures around 1273 K. For the $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ samples prepared at, 15GPa and 1573 K, grain growth is greater for $x = 0.5$ than for $x = 0.3$ and 0.7 suggesting that the minimum melting point in the $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ series is near $x = 0.5$.

Initial Rietveld fits to the XRD profiles showed that strong textures were present in the loosely packed powders and so another pattern was collected from each sample sieved onto a greased surface to minimise this effect. Large differences between the two patterns for each sample are evident in Fig. 2. Fits to the greased samples were used to refine the crystal structure parameters, giving the results shown in Table 2. The variation of lattice parameters with composition in the $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ series is shown in Fig. 4, taking results for CaPtO_3 from ref. 5. It is notable that the a - and b -axis lengths change linearly with composition, whereas the c -axis shows curvature and lies below the values expected by linear interpolation between the end-members for $0 < x < 1$. This leads to the same trend in the cell volume. This non-linearity

suggests that some local ordering of Ir/Pt occurs within the chains of corner-sharing octahedra along the *c*-direction of the crystal structure (Fig. 1).

The Ir/Pt/RhO₆ octahedra show a tetragonal compression in all CaIr_{1-x}Pt_xO₃ structures, and in CaIr_{0.5}Rh_{0.5}O₃, with two short M-O1 (1.91-1.99 Å) and four long M-O2 (2.04-2.09 Å) bonds (Table 2). This is not consistent with a Jahn-Teller distortion of low spin 5d⁵ Ir⁴⁺, as tetragonal elongation is needed to break the electronic degeneracy. The connectivity of the post-perovskite structure provides a likely explanation. Applying the bond valence principle that the summed valences of the bonds around a cation or anion should equal the formal valence, gives M-O1 and M-O2 valences of 12/17 (≈0.71) and 11/17 (≈0.65) respectively, showing that the M-O1 bonds are expected to be slightly stronger and shorter than the M-O2. These values compare well to bond valences in Table 2 calculated from the standard function $\exp((d_i - d_0)/B)$ and parameters,¹⁶ where d_i is the bond distance, d_0 is a constant for a particular atom pair and $B = 0.37$ Å. Appropriate averages of d_0 constants were used for Ir/Pt and Ir/Rh solid solutions and the M site Bond Valence Sums (BVS's) are close to the expected +4 value. The anisotropy of the structure also results in strained CaO₈ polyhedra, with BVS's between 2.1 and 2.4. Hence, the primary octahedral distortion in the CaMO₃ post-perovskites is driven by the anisotropic bonding network rather than by electronic instabilities of the d-electron configuration. However, a small electronic influence is evident by calculating the octahedral distortion parameter $\Delta d = 1/6\{2(d_1 - d)^2 + 4(d_2 - d)^2\}/d^2$ (d_1 : M-O1 bond distance, d_2 : M-O2 bond distance, d : average M-O distance)¹⁵. Fig. 4(e) shows that Δd decreases across the CaIr_{1-x}Pt_xO₃ series as the triply degenerate ground state of low spin 5d⁵ Ir⁴⁺ is replaced by non-degenerate 5d⁶ Pt⁴⁺. No systematic changes in the O-M-O angles or M-O-M angles (Table 2) are evident in the CaIr_{1-x}Pt_xO₃ series.

To obtain morphological information from the XRD patterns of loosely packed powders, the crystal structure parameters were fixed at the values obtained from the greased samples, and the intensities were Rietveld-fitted by varying the six ODF (Orientation Density Function) coefficients that describe a cylindrical symmetry sample texture up to 4th order.¹⁶ This gave a good fit to the peak intensities as shown in Fig. 2. The orientation densities derived from the refined ODF parameters are shown in Fig. 5. These show the density of crystallites with plane (hkl) at an angle ψ to the sample plane, relative to the average (untextured) value of 1.0. In all samples the maximum density for (100) is at $\psi = 90^\circ$, confirming that the crystallographic *a*-axis is parallel to the long dimension of the needle-like crystals. The (010) and (001) densities are consequently both peaked at $\psi = 0$ but a systematic change from (001) to (010) density is observed as *x* increases from *x* = 0 to 0.7. This shows that Pt substitution favours (001) over (010) growth. The magnitudes of the orientation density maxima in the CaIr_{1-x}Pt_xO₃ series correlate well

with the grain sizes observed by SEM. The large grain CaIrO_3 and $\text{CaIr}_{0.5}\text{Pt}_{0.5}\text{O}_3$ show maximum densities of near 3, whereas the smaller-grained $\text{CaIr}_{0.7}\text{Pt}_{0.3}\text{O}_3$ and $\text{CaIr}_{0.3}\text{Pt}_{0.7}\text{O}_3$ have density maxima of 1.4 and 2.1 respectively. However, the $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ sample shows the most extreme texture with an (001) density of 4.0 at $\psi = 0$.

B Electronic and Magnetic Properties

The temperature dependences of electrical resistivity for CaIrO_3 , $\text{CaIr}_{0.5}\text{Pt}_{0.5}\text{O}_3$ and $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ are shown in Fig. 6. The samples are narrow bandgap semiconductors with bandgap energies of 34-150 meV (Table 3) estimated from the 290 K gradient of Arrhenius plots.

Fig. 7 shows the temperature dependence of magnetic susceptibility for the five samples. A ferromagnetic transition, marked by an upturn in magnetisation and divergence of zero-field and field cooled susceptibilities, is observed for CaIrO_3 at $T_C = 108$ K which is comparable to a previously reported value.¹² Transitions are seen at the same temperature for all the $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ solid solutions showing that traces of CaIrO_3 are present, although these were not observed in the EDX analyses. The intrinsic transition is suppressed to 20 K for $x = 0.3$ and is not observed down to 5 K for the $x = 0.5$ and 0.7 samples. $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ shows the ferromagnetic transition at 40 K. Hence both Pt and Rh substitutions suppress the magnetic transition in CaIrO_3 with a more rapid suppression by diamagnetic Pt^{4+} than by magnetic Rh^{4+} .

The 150-300 K inverse susceptibilities are shown in the insets to Fig. 7. CaIrO_3 shows temperature-independent paramagnetism over this range but the other samples have non-linear susceptibilities. These were fitted using the equation $1/\chi = [\alpha + C/(T-\theta)]^{-1}$ which combines temperature-independent and Curie-Weiss terms. The fitted curves are shown on Fig. 7 and the derived parameters are in Table 3. These show that CaIrO_3 appears to be close to a metal-insulator transition, as it shows only temperature-independent paramagnetic behaviour at high temperatures despite appearing non-metallic. Doping with Pt suppresses the near-metallic behaviour as the resistivity increases by six orders of magnitude for $x = 0.5$, decreases the temperature-independent paramagnetism, and gives rise to local moments, although Pt^{4+} is diamagnetic. These follow Curie-Weiss behaviour with an effective paramagnetic moment of $\sim 0.5 \mu_B/\text{formula unit}$ and the positive Weiss constants evidence ferromagnetic exchange interactions between spins. In contrast, $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ has a small negative θ , although this is almost within error of zero.

Magnetisation-field data for CaIrO_3 , $\text{CaIr}_{0.7}\text{Pt}_{0.3}\text{O}_3$ and $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ are shown in Fig. 8. Ferromagnetic hysteresis loops are observed for the former two materials but $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ appears to have only short range ferromagnetic interactions. CaIrO_3 is an unusually hard magnetic

oxide, with a large magnetic anisotropy and a coercive field of $H_c = 3.4\text{T}$ at 5K for the present sample. The thermal evolution of the hysteresis loop is also shown in Fig. 8(a). The variation of the coercive field with temperature (Fig. 9) was fitted with the equation¹⁷: $H_c = 2\alpha K/M_s[1 - (T/T_C)^{1/2}]$ where $\alpha = 0.48$, and the fitted uniaxial anisotropy constant is $K = 1.77 \times 10^6 \text{ Jm}^{-3}$. This is comparable to the value of $5 \times 10^6 \text{ Jm}^{-3}$ for $\text{Nd}_2\text{Fe}_{14}\text{B}$ which is a widely used permanent magnet material.^{18, 19} The large crystal field and the strong spin-orbital coupling of $\text{Ir}^{4+} (5d^5)$, as found in a recent study on Sr_2IrO_4 ,¹⁹ and the anisotropic crystal structure and morphology of CaIrO_3 are all likely contributors to this exceptionally high coercivity for a magnetic oxide. Substitution of 30% Pt for Ir dilutes the magnetic interactions and decreases the saturated magnetisation from 0.040 $\mu_B/\text{formula unit}$ for CaIrO_3 to 0.024 $\mu_B/\text{formula unit}$, while the 5K coercive field drops to 0.46T.

IV. Discussion

To date, the only quenchable oxides having the post-perovskite (CaIrO_3) structure are CaMO_3 for $M = \text{Ru, Rh, Ir and Pt}$. These M^{4+} cations are very similar, having a narrow range of ionic radii (0.60-0.625 Å)²⁰ and large octahedral crystal field stabilisation energies resulting from their low spin d^n ($n = 4-6$) electron configurations. A recent DFT study¹⁵ of CaRhO_3 suggested that metal-metal bonding in the chains of edge-shared octahedra parallel to the a -axis, as found in the rutile types RuO_2 ²¹, IrO_2 ²², RhO_2 ^{15,16} and ReO_2 ,²³ also plays a role. This may account for the ambient pressure stability of post-perovskite CaIrO_3 , which has a formal Ir^{4+} - Ir^{4+} bond order of one, in comparison to CaPtO_3 for which the Pt^{4+} - Pt^{4+} bond order is zero. This analysis predicts that CaReO_3 post-perovskite (Re^{4+} radius = 0.63 Å) should also be accessible (but initial syntheses up to 25 GPa and 1400 K have not proved successful). As the stability conditions for post-perovskite oxides are rather severe, it is useful to explore solid solutions between these end-members to increase the range of available materials.

This study has demonstrated that the full series of $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ solid solutions can be stabilised, and the recovery of $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ suggests that the $\text{CaIr}_{1-x}\text{Rh}_x\text{O}_3$ series should also be accessible. However, the synthesis pressures (~15 GPa) required to give near-homogenous $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ solid solutions were found to be far higher than those to prepare the end-members (1 bar and 4 GPa for $x = 0$ and 1, respectively). Although x-ray diffraction, EDX analysis and Raman spectroscopy indicate that the $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ samples are homogenous, the magnetic measurements show that traces of CaIrO_3 are present.

A pronounced grain growth in the [100] direction is observed for all the samples in this study. This growth gives rise to a large preferred orientation even in loosely packed powders, and anchoring the particles on a greased surface was required to give XRD data suitable for structure

analysis. To the first approximation, no structural change is expected across the $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ series as Ir^{4+} and Pt^{4+} have identical ionic radii of 0.625 Å. However, some small changes in the lattice parameters and volume are observed experimentally, with evidence for possible local Ir/Pt order from the curvature in the c-parameter variation. The MO_6 octahedra are intrinsically distorted due to the anisotropic connectivity in the post-perovskite arrangement, but the loss of Jahn-Teller effects reduces the distortion of the MO_6 octahedra as x increases in the $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ series.

The electronic ground state of CaIrO_3 appears unconventional as the bulk electronic behaviour is semiconducting but the high temperature susceptibility has a temperature-independent variation. This could indicate an intrinsic Pauli paramagnetic and metallic behaviour, masked by resistive grain boundaries in the ceramic samples. Alternatively, the ground state may be gapped, with Ir-Ir bonding and spin-orbit coupling effects resulting in a near-zero Ir^{4+} magnetic moment. Strong spin-orbital coupling has been reported in Sr_2IrO_4 .²⁴ The small ferromagnetic moment of 0.04 μ_B could be consistent with Stoner magnetism in a marginally metallic state, or canted order of larger, localised moments. Curie-Weiss paramagnetism emerges as CaIrO_3 is doped with non-magnetic Pt^{4+} or magnetic Rh^{4+} which suggests that disruption of a narrow Ir-Ir bonding band may be the dominant effect. The Curie transition is suppressed to zero at $x \approx 0.4$ for Pt-doping (assuming a linear $T_C(x)$ variation) but $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ has $T_C = 40$ K showing a clear dependence of the suppression on the magnetic nature of the dopants. The 290 K resistivity of $\text{CaIr}_{0.5}\text{Pt}_{0.5}\text{O}_3$ is six orders of magnitude greater than for CaIrO_3 whereas that of $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ is almost unchanged, consistent with the loss of hole carriers in the Ir d-band through Pt-doping.

Post-perovskite CaIrO_3 is also notable for having a very large magnetic anisotropy, comparable to that of hard magnetic materials such as $\text{Nd}_2\text{Fe}_{14}\text{B}$. This demonstrates that permanent magnets could be made from post-perovskites containing transition metals with larger spins.

Acknowledgements

We thank EPSRC and the Leverhulme Trust for support.

References

-
- ¹ Murakami, M; Hirose, K; Kawamura, K; Sata, K; Ohishi, Y *Science*, 2004, 304, 855-858
 - ² Shim, S; Bengtson, A; Morgan, D; Sturhahn, W; Catalli, K; Zhao, J; Lerche, M; Prakapenka, V.B. *PNAS*, **2009**, 106, 5508-5512

-
- ³ Santillán, J; Shim, S; Shen, G; Prakapenka, V.B. *Geophys. Res. Lett.*, **2006**, 33, L15307
- ⁴ Hirai, S; Welch, M.D; Aguado, F; Redfern, S.A.T. *Z. Kristallogr.*, **2009**, 224, 345-350
- ⁵ Ohgushi, K; Matsushita, Y; Miyajima, N; Katsuya, Y; Tanaka, M; Izumi, F; Gotou, H; Ueda, Y; Yagi, T. *Physics and Chemistry of Minerals*, **2008**, 35, 189-195
- ⁶ Yamaura, K; Shirako, Y; Kojitani, H; Arai, M; Young, D.P.; Akaogi, M; Nakashima, M; Katsumata, T; Inaguma, Y; Takayama-Muromachi, E. *J. Am. Chem. Soc.*, **2009**, 131, 2722-2726
- ⁷ Kojitani, H; Shirako, Y; Akaogi, M. *Physics of the Earth and Planetary Interiors*, **2007**, 165, 127-134
- ⁸ Kojitani, H; Furukawa, A; Akaogi, M. *Am. Mineral.*, **2007**, 92, 229-232
- ⁹ Inaguma, Y; Hasumi, K; Yoshida, M; Ohba, T; Katsumata, T. *Inorg. Chem.*, **2008**, 47, 1868-1870
- ¹⁰ Hustoft, J; Shim, S; Kubo, A; Nishiyama, N. *Am. Mineral.*, **2008**, 93, 1654-1658
- ¹¹ Lindsay-Scott, A; Wood, I.G.; Dobson D.P.; Vočadlo, L; Brodholt, J.P.; Crichton, W; Hanfland, M; Taniguchi, T. *Physics of the Earth and Planetary Interiors*, **2010** to be published
- ¹² Ohgushi, K; Gotou, H; Yagi, T; Kiuchi, Y; Sakai, F; Ueda, Y. *Phys. Rev. B*, **2006**, 74, 241104
- ¹³ Larson, A.C.; Von Dreele, R.B. *Los Alamos National Laboratory Report LAUR*, **2000**, 86-748
- ¹⁴ Miyajima, N; Ohgushi, K; Ichihara, M; Yagi, T. *Geophys. Res. Lett.*, **2006**, 33, L12302
- ¹⁵ Alonso, J.A.; Martinez-Lope, M.J.; Casais, M.T. *Inorg. Chem.*, **2000**, 39, 917-923
- ¹⁶ Von Dreele, R.B. *J. Appl. Crystallogr.*, **1997**, 30, 517-525
- ¹⁷ Nunes, W.C.; Folly, W.S.D; Sinnecker, J.P.; Novak, M.A. *Phys. Rev. B.*, **2004**, 70, 014419
- ¹⁸ Blundell, S. *Magnetism in Condensed Matter*, **2001**, 128-136
- ¹⁹ Haskel, D; Lang, J. C.; Islam, Z.; Cady, A; Srajer, G; Veenendaal, M; Canfield, P.C. *Phys. Rev. Lett.*, **2005**, 95, 217207
- ²⁰ Shannon, R.D.; *Acta Cryst.*, **1976**, A32, 751-767
- ²¹ Grillo, M.E. *Comput. Mater. Sci.*, **2005**, 33, 83-91
- ²² Shimony, Y; Ben-dor, L. *J. Mater. Sci. Lett.*, **1983**, 2, 558-560
- ²³ Ivanovskii, A.L.; Chupakhina, T.I.; Zubkov, V.G; Tyutyunnik, A.P.; Krasilnikov, V.N.; Bazuev, G.V.; Okatov S.V.; Lichtenstein, A.I. *Phys. Lett. A*, **2005**, 348, 66-70
- ²⁴ Kim, B.J.; Jin, H; Moon, S.J.; Kim, J.Y.; Park, B.G.; Leem, C.S.; Yu, J; Noh, T.W.; Kim, C; S.-J. Oh, S.J.; Park, J.H.; Durairaj, J; Cao, G; Rotenberg, E. *Phys. Rev. Lett.*, **2008**, 101, 076402

Table 1: Frequencies of the five primary Raman modes of $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ and $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$.

Frequency (cm^{-1})	CaIrO_3	$\text{CaIr}_{0.7}\text{Pt}_{0.3}\text{O}_3$	$\text{CaIr}_{0.5}\text{Pt}_{0.5}\text{O}_3$	$\text{CaIr}_{0.3}\text{Pt}_{0.7}\text{O}_3$	$\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$
ν_1	309	322	320	334	301
ν_2	444	452	451	452	449
ν_3	552	543	544	553	546
ν_4	-----	562	559	568	565
ν_5	712	688	692	703	648

Table 2: Average grain sizes and crystallographic results* for $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ and $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$.

Compounds	CaIrO_3	$\text{CaIr}_{0.7}\text{Pt}_{0.3}\text{O}_3$	$\text{CaIr}_{0.5}\text{Pt}_{0.5}\text{O}_3$	$\text{CaIr}_{0.3}\text{Pt}_{0.7}\text{O}_3$	$\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$
Grain size (μm)	8.0	1.0	8.0	2.0	3.0
a (\AA)	3.14592(4)	3.14114(7)	3.13575(7)	3.13216(4)	3.11997(6)
b (\AA)	9.8635(1)	9.8795(2)	9.8924(1)	9.9051(1)	9.8652(1)
c (\AA)	7.29903(9)	7.3081(1)	7.3169(1)	7.3303(1)	7.2930(1)
V (\AA^3)	226.489(6)	226.795(12)	226.973(9)	227.420(7)	224.476(8)
R_{wp}	0.0560	0.0350	0.0359	0.0337	0.0634
χ^2	1.17	1.17	1.20	1.08	1.62
Ca: y	0.2503(3)	0.2474(6)	0.2510(5)	0.2500(4)	0.2484(4)
O1: y	0.425(1)	0.439(2)	0.429(2)	0.421(1)	0.441(2)
O2: y	0.1320(8)	0.127(1)	0.128(1)	0.1291(8)	0.132(1)
O2: z	0.4455(9)	0.451(2)	0.449(1)	0.450(1)	0.435(1)
U_{iso} (\AA^2)	0.0024(5)	0.0131(6)	0.0009(5)	0.0037(6)	0.0077(9)
M-O1 (\AA)	1.967(5) x2	1.923(5) x2	1.957(7) x2	1.993(5) x2	1.913(5) x2
M-O2 (\AA)	2.081(5) x4	2.041(7) x4	2.053(7) x4	2.055(6) x4	2.087(7) x4
$\langle\text{M-O}\rangle$ (\AA)	2.041(5)	1.999(6)	2.019(7)	2.032(6)	2.026(6)
M-O1 valence	0.77(1)	0.87(1)	0.80(2)	0.73(1)	0.87(1)
M-O2 valence	0.56(1)	0.63(1)	0.62(1)	0.62(1)	0.55(1)
BVS(Ir)	3.78(6)	4.26(6)	4.08(8)	3.94(6)	3.94(6)
M-O1-M ($^\circ$)	136.1(7)	143.7(9)	138(1)	133.7(7)	145(1)
M-O2-M ($^\circ$)	98.2(3)	100.6(5)	99.6(4)	99.3(4)	96.8(4)
O1-M-O2 ($^\circ$)	93.3(3)	91.3(4)	92.8(5)	94.5(3)	91.6(4)
O2-M-O2 ($^\circ$)	98.2(3)	100.6(5)	99.6(4)	99.3(4)	96.8(4)

*Atomic positions; Ca: 4c (0, y, 1/4), M = Ir/Pt/Rh: 4a (0, 0, 0), O1: 4c (0, y, 1/4), O2: 8f (0, y, z); bond valences of M-O bonds were calculated as $\exp((d_i - d_0)/B)$ with d_0 values of 1.870 ($\text{Ir}^{4+}\text{-O}^{2-}$), 1.879 ($\text{Pt}^{4+}\text{-O}^{2-}$), 1.857 ($\text{Rh}^{4+}\text{-O}^{2-}$).

Table 3: Electronic and magnetic parameters of $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ and $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$

Compounds	CaIrO_3	$\text{CaIr}_{0.7}\text{Pt}_{0.3}\text{O}_3$	$\text{CaIr}_{0.5}\text{Pt}_{0.5}\text{O}_3$	$\text{CaIr}_{0.3}\text{Pt}_{0.7}\text{O}_3$	$\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$
E_g (eV)	0.14	-	0.15	-	0.034
$\rho_{290\text{K}}$ (Ωcm)	10.1	-	8.37×10^6	-	6.79
α (emu.mol^{-1})	0.00748(1)	0.00024(2)	0.00126(1)	0.00043(1)	0.00043(1)
θ (K)	-	37(11)	87(7)	39(8)	-16(12)
C (emu.K.mol^{-1})	-	0.053(9)	0.02(1)	0.031(7)	0.028(9)
μ_{eff} ($\mu_B/\text{f.u.}$)	-	0.7(3)	0.4(3)	0.5(2)	0.5(3)
T_c (K)	108	20	-	-	40

Fig.1: Crystal structure of post-perovskite type CaIrO_3 showing layers of edge- and corner-sharing IrO_6 octahedra, separated by Ca ions.




Fig.2: Fitted powder X-ray diffraction profiles of (a) CaIrO_3 and (b) $\text{CaIr}_{0.5}\text{Pt}_{0.5}\text{O}_3$ (upper/lower panels are for powdered samples on greased/ungreased holders, showing considerable texture effects in the latter).




Fig.3: Typical SEM image of grains of $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ for (a) $x = 0$ (scale bar = $20\text{ }\mu\text{m}$), (b) $x = 0.3$ ($5\text{ }\mu\text{m}$), (c) $x = 0.5$ ($10\text{ }\mu\text{m}$), (d) $x = 0.7$ ($10\text{ }\mu\text{m}$), and of (e) $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ ($10\text{ }\mu\text{m}$).

(a) (b)

(c) (d)

(e)




Fig. 4: Evolution of the orthorhombic lattice parameters, unit cell volume (V) and octahedral distortion parameter Δd , as defined in the text, for $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ solid solutions. The fitted curves are guides to the eye.




Fig. 5: Angular dependence of crystallite orientation density of $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ for (a) $x = 0$, (b) $x = 0.3$, (c) $x = 0.5$ (d) $x = 0.7$, and of (e) $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$.




Fig.6: Temperature dependence of electrical resistivity for $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$, CaIrO_3 and $\text{CaIr}_{0.5}\text{Pt}_{0.5}\text{O}_3$.




Fig.7: ZFC and FC (open and closed symbols) magnetic susceptibilities (M/H) of $\text{CaIr}_{1-x}\text{Pt}_x\text{O}_3$ for (a) $x = 0$, (b) $x = 0.3$, (c) $x = 0.5$, (d) $x = 0.7$, and of (e) $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$. Insets show fits to inverse susceptibilities between 150 and 300 K.




Fig.8: Magnetization-field hysteresis loops for (a) CaIrO_3 at temperatures between 5 and 105 K, (b) $\text{CaIr}_{0.7}\text{Pt}_{0.3}\text{O}_3$ at 5 K, and (c) $\text{CaIr}_{0.5}\text{Rh}_{0.5}\text{O}_3$ at 5 K.




Fig.9: Temperature dependence of the coercive field for CaIrO_3 showing the fit described in the text.

